

RELIABILITY REPORT FOR

DS1020, Rev B5

Dallas Semiconductor

4401 South Beltwood Parkway Dallas, TX 75244-3292

Prepared by:

Ken Wendel

Ken Wendel Reliability Engineering Manager Dallas Semiconductor 4401 South Beltwood Pkwy. Dallas, TX 75244-3292

Email: ken.wendel@dalsemi.com

ph: 972-371-3726 fax: 972-371-6016 mbl: 214-435-6610

Conclusion:

The following qualification successfully meets the quality and reliability standards required of all Dallas Semiconductor products and processes:

In addition, Dallas Semiconductor's continuous reliability monitor program ensures that all outgoing product will continue to meet Maxim's quality and reliability standards. The current status of the reliability monitor program can be viewed at http://www.maxim-ic.com/TechSupport/dsreliability.html.

Device Description:

A description of this device can be found in the product data sheet. You can find the product data sheet at http://dbserv.maxim-ic.com/l_datasheet3.cfm.

Reliability Derating:

The Arrhenius model will be used to determine the acceleration factor for failure mechanisms that are temperature accelerated.

```
AfT = exp((Ea/k)*(1/Tu - 1/Ts)) = tu/ts
AfT = Acceleration factor due to Temperature
tu = Time at use temperature (e.g. 55°C)
ts = Time at stress temperature (e.g. 125°C)
k = Boltzmann's Constant (8.617 x 10-5 eV/°K)
Tu = Temperature at Use (°K)
Ts = Temperature at Stress (°K)
Ea = Activation Energy (e.g. 0.7 ev)
```

The activation energy of the failure mechanism is derived from either internal studies or industry accepted standards, or activation energy of 0.7ev will be used whenever actual failure mechanisms or their activation energies are unknown. All deratings will be done from the stress ambient temperature to the use ambient temperature.

An exponential model will be used to determine the acceleration factor for failure mechanisms, which are voltage accelerated.

```
AfV = exp(B*(Vs - Vu))
AfV = Acceleration factor due to Voltage
Vs = Stress Voltage (e.g. 7.0 volts)
Vu = Maximum Operating Voltage (e.g. 5.5 volts)
B = Constant related to failure mechanism type (e.g. 1.0, 2.4, 2.7, etc.)
```

The Constant, B, related to the failure mechanism is derived from either internal studies or industry accepted standards, or a B of 1.0 will be used whenever actual failure mechanisms or their B are unknown. All deratings will be done from the stress voltage to the maximum operating voltage. Failure rate data from the operating life test is reported using a Chi-Squared statistical model at the 60% or 90% confidence level (Cf).

The failure rate, Fr, is related to the acceleration during life test by:

```
Fr = X/(ts * AfV * AfT * N * 2)
X = Chi-Sq statistical upper limit
N = Life test sample size
```

Failure Rates are reported in FITs (Failures in Time) or MTTF (Mean Time To Failure). The FIT rate is related to MTTF by:

MTTF = 1/Fr

NOTE: MTTF is frequently used interchangeably with MTBF.

The calculated failure rate for this device/process is:

FAILURE RATE: MTTF (YRS): 54920 FITS: 2.1

The parameters used to calculate this failure rate are as follows:

Cf: 60% Ea: 0.7 B: 0 Tu: 25 °C Vu: 5.5 Volts

The reliability data follows. A the start of this data is the device information. The next section is the detailed reliability data for each stress. The reliability data section includes the latest data available and may contain some generic data.

Device Information:

Process: 1P, 1M, 1.5um, MedR P1, NdplDiode , TEOS Spacer,

Passivation: Laser/Nit - Pass/Nit - General LaserPrb

Die Size: 170 x 115 Number of Transistors: 5381

Interconnect: Aluminum / 1% Silicon / 0.5% Copper

Gate Oxide Thickness: 250 Å

OPERATING LIFE						
DESCRIPTION	DATE CODE	CONDITION	READ	POINT	QUANTITY	FAILS
HIGH VOLTAGE LIFE	9512	125C, 7.0 VOLTS	1000	HRS	153	0
		125C, 7.0 VOLTS	1000	HRS	153	0
INFANT LIFE	9522	125C, 6.0 VOLTS	48	HRS	77	0
		125C, 6.0 VOLTS	48	HRS	77	0
HIGH VOLTAGE LIFE	9522	125C, 6.0 VOLTS	1000	HRS	77	0
		125C, 6.0 VOLTS	1000	HRS	77	0
				Total:		0

FAILURE RATE: MTTF (YRS): 54920 FITS: 2.1